

**CQUARTZ****CQUARTZ UK****CQP****CQFR****Skin****Leather****Lite****DURABILITY**

(handwash only)

**2 LAYERS**

18 months

24 months

&gt;24 months

&gt;36 months

12 months

12 months

&gt;6 months

**3 LAYERS**

18 months

24 months

&gt;24 months

&gt;36 months

12 months

12 months

&gt;6 months

**PH-RESISTANCE**

3~12

3~13

3~13

3~13

5~12

5~12

3~13

**FLASHINGTIME**

(flash time may vary on room temp and humidity)

30~60 sec

30~60 sec

3~5 min

3~4 min

2~3 min

no flash

0 sec

**MIN AND MAX TIME BETWEEN LAYERS**

1 hour

1 hour

4 hours

4 hours

1 hour

4 hours

1 hour

**DRYINGTIME UNTIL WATER CONTACT**

24h

24h

24h

24h

24h

24h

24h

**DRYINGTIME UNTIL FULL HARDNESS**

7 days

7 days

7 days

7 days

7 days

7 days

7 days

**IR LAMP YES/NO, IMPROVEMENT**

yes

yes

yes

yes

no

no

yes

**IR TIME&TEMP**

60°C / 10 min

60°C / 10 min

60°C / 10 min

60°C / 10 min

60°C / 10 min

60°C / 10 min

60°C / 10 min

**HARDNESS IMPROVEMENT**

(hardness depends allot on the clearcoat)

up to 2h

up to 2h

up to 2h

up to 2h

0

0

up to 2h

**WATER SPOT SENSITIVITY**

high

high

low

low

low

high

**CHEMICAL REMOVABLE WITH?**

polishing

polishing

polishing

polishing

solvent mixture

high pH brushing

polishing

**GLOSS**

high

high

high

high

high

high

**SMOOTHNESS**

medium

medium

high

high

high

medium

medium



	DLUX	Fabric	HydroO2	Elixir	Reload	Gliss	Forte	Flyby30	
<b>DURABILITY</b> (handwash only)	<b>2 LAYERS</b>	12 months	6 months	3 months	1 month	3 months	12 months	12 months	3 months
	<b>3 LAYERS</b>	12 months	6 months	3 months	1 month	3 months	12 months	12 months	3 months
<b>PH-RESISTANCE</b>	5~12	5~12	6~7	6~7	6~7	5~12	5~12	5~12	
<b>FLASHINGTIME</b> (flash time may vary on room temp and humidity)	30~60sec	no flash	10 sec	no flash	no flash	1~2 min	30 sec	30~60sec	
<b>MIN AND MAX TIME BETWEEN LAYERS</b>	1 hour	no minimum	no minimum	no minimum	no minimum	1 hour	4 hours	1 hour	
<b>DRYINGTIME UNTIL WATER CONTACT</b>	24h	24h	0	0	0	24h	24h	24h	
<b>DRYINGTIME UNTIL FULL HARDNESS</b>	7 days	48h	0	0	0	7 days	7 days	7 days	
<b>IR LAMP YES/NO, IMPROVEMENT</b>	yes	yes	no	no	no	yes	yes	yes	
<b>IR TIME&amp;TEMP</b>	60°C / 10 min	60°C / 10 min				60°C / 10 min	60°C / 10 min	60°C / 10 min	
<b>HARDNESS IMPROVEMENT</b> (hardness depends allot on the clearcoat)	0	0				0	0	0	
<b>WATER SPOT SENSITIVITY</b>	low		medium	low	low	low	medium	medium	
<b>CHEMICAL REMOVABLE WITH?</b>	high pH clean	high pH clean	high pH clean	high pH clean	high pH clean	polishing	polishing	polishing	
<b>GLOSS</b>			high	high	high	high			
<b>SMOOTHNESS</b>	medium		medium	high	high	high	low	low	